

Autolab Application Note EC14


Oxygen Reduction Reaction with the Rotating Ring Disk Electrode

Keywords


RRDE, ORR, hydrodynamic conditions, LSV, Levich analysis, Koutecký-Levich analysis.

Summary

The oxygen reduction reaction (ORR) is one of the most studied reactions in the field of electrocatalysis. The ORR in aqueous acidic electrolyte can proceed through different pathways depending on the reaction conditions. In most cases, the desired reaction is the 4-electron process shown in equation 1. Other possible reaction pathways include the combinations of equations 2 and 3, where H₂O₂ is formed as an intermediate, and equations 2 and 4, where the reduction is incomplete.



If hydrogen peroxide (H₂O₂) is formed as a product or intermediate during the ORR, it can be detected electrochemically through its oxidation reaction (equation 5).



The ORR is generally studied in hydrodynamic conditions using a rotating working electrode (WE) to induce forced convection within the electrochemical cell. This strategy is applied to achieve a stable mass transfer limited current density that may otherwise be difficult to maintain because of the slow kinetics of the reaction. In this application note, a rotating ring disk electrode (RRDE) set up is used to study the ORR.

Experimental Conditions

An Autolab PGSTAT302N potentiostat/galvanostat fitted with the BA module, a dual-mode bipotentiostat, was used in combination with the Autolab RRDE hardware. The measurements were carried out in a four electrode

configuration using the Autolab RRDE electrochemical cell. Since the electrochemical signals from Pt electrodes are sensitive to system impurities, all cell components in contact with the electrolyte were thoroughly cleaned. The cleaning procedure consists of soaking the components a diluted solution of H₂SO₄ with H₂O₂, followed by rinsing several times with boiling water. The working electrodes were the Pt disk (WE1) and Pt ring (WE2), which are both built into a single RRDE tip. The RRDE tips have a theoretical collection efficiency of 24.9% based on the geometry of the disk and the ring. Determination of the experimental collection efficiency and the meaning of the theoretical collection efficiency value are outside the scope of this application note. The counter electrode (CE) was a platinum sheet and the reference electrode (RE) was a double junction Ag/AgCl electrode with 3M aqueous KCl solution in the inner compartment and the working electrolyte (0.5 M H₂SO₄) in the outer compartment. Both the CE and the RE were inserted into the cell at a height slightly above that of the bottom of the RRDE electrode tip in order to avoid disturbing the hydrodynamic flow profile. The 0.5 M H₂SO₄ electrolyte was purged with high purity O₂ gas for fifteen minutes prior to beginning the experiments in order to reach a saturated concentration of dissolved O₂. During the measurement, a blanket of O₂ gas was maintained over the surface of the electrolyte to ensure that the concentration of dissolved O₂ remained stable.

The experimental procedure *hydrodynamic linear sweep with RRDE* was applied using in Nova 2.1 software. At the disk, linear voltammetry staircase sweeps from 0.70 to -0.20 V vs. Ag / AgCl were applied with various electrode rotation rates (ω). At the ring, the potential was fixed at 1.00 V and the current response was recorded.

Experimental Results

Figure 1 shows the results of a typical ORR RRDE experiment. The blue curves correspond to the current at the Pt disk (WE1) as the E is swept from 0.70 to -0.20 V at a scan rate of 50 mV s⁻¹ with various electrode rotation rates (ω). The red curves correspond to the current signal at the Pt ring (WE2), whose potential is fixed at a value of 1.00 V, at the same ω values as the disk. The ω values varied between 500 and 3000 RPM; they were chosen with a square







Figure 1. Plot of the disk (solid lines) and ring (dashed lines) data collected during the hydrodynamic RRDE study of the ORR using a Pt disk and Pt ring. The Pt disk potential was swept at a scan rate of 50 mV s^{-1} ; the ring potential was fixed at $1.00 \text{ V vs. Ag/AgCl}$. Electrode rotation rates between 500 and 3000 RPM were applied.

root relationship for intuitive representation on the Levich plot. As the potential at the disk is swept from high to low values, the onset of ORR gives rise to a negative (cathodic) signal that is observable at approximately 0.65 V .

The current increases with decreasing potential then reaches a plateau region at approximately $E = 0.20$ to -0.10 V . This plateau is also known as the *mass transfer limited region* of the voltammetry profile where the rate of the ORR reaction is limited by the availability of oxygen at the electrode surface. The cathodic current increases in magnitude with increasing ω according to the Levich relationship. At the lowest potential values (i.e. lower than -0.10 V), cathodic current decreases in magnitude as the adsorption of hydrogen on the Pt electrode surface interferes with the ORR. The potential at the ring is fixed at 1.00 V , thus the x-axis of the graph in Figure 1 does not apply to the ring data. Although the potential of the ring is fixed, the current signal at the ring changes as the potential of the disk is swept. This is because the disk and the ring are in close proximity of each other (there is a separation of $375 \mu\text{m}$ between the disk and ring). Thus, the chemical environment at the disk influences the ring. As oxygen is reduced at the disk, reaction products, such as H_2O_2 , diffuse from the disk to the ring and may undergo further reaction. The oxidation of H_2O_2 gives rise to a positive (anodic) current signal and therefore the current at the ring is indicative of H_2O_2 production at the disk. The anodic current at the ring increases as the potential of the disk is swept to low values that give rise to ORR at a significant rate. When the disk current is limited by mass transfer (plateau region of the blue curves), the current corresponding to H_2O_2 oxidation at the ring continues at a relatively stable value. When the cathodic disk current decreases due to the presence of adsorbed hydrogen on its surface, the ring current increases sharply; this indicates a change in the ORR mechanism where a



greater proportion of the reaction is now following a pathway that favors H_2O_2 production.

Figure 2. Linear sweep voltammetry profiles (top) from the disk electrode at various rotation rates; the potential value for the Levich and Koutecký-Levich analyses are indicated. Levich (middle) and Koutecký-Levich (bottom) plots.

Figure 2 shows the Levich and Koutecký-Levich plots for the ORR which demonstrate the relationship between the current and the rotation rate at a fixed potential. When the potential value is selected within the mass-transfer limiting plateau of the I vs. E curves, the Levich plot follows a linear relationship according to equation 6.

$$i_l = 0.62 \times n F D^{2/3} \nu^{-1/6} C \sqrt{\omega} \quad (6)$$

When the potential is selected from the region where the current is under a mixture of kinetic and mass transfer control, the Koutecký-Levich plot is linear according to equation 7.

$$\frac{1}{i} = \frac{1}{i_k} + \frac{1}{0.62 \times n F D^{2/3} \nu^{-1/6} C \sqrt{\omega}} \quad (7)$$

For both equations 6 and 7, the variables are defined as:

A is the geometric area of the disk (cm^2)

F is Faraday's constant (C mol^{-1})

D is the diffusion coefficient of O_2 in the electrolyte ($\text{cm}^2 \text{s}^{-1}$)

ν is the kinematic viscosity of the electrolyte ($\text{cm}^2 \text{s}^{-1}$)

C is the concentration of O_2 in the electrolyte (mol cm^{-3})

ω is the angular frequency of rotation (rad s^{-1})

n is the number of electrons involved in the reaction

The Levich and the Koutecký-Levich plots can be fitted using linear regression to calculate the slopes and intercepts. For the Koutecký-Levich plot, the kinetic current (i_k) is calculated from the y-intercept which is equal to $1/i_k$. According to equation 8, the i_k value can be related to the rate constant for electron transfer (k). In order for equation 8 to be applied, the number of electrons involved in the reaction (n) must be known.

$$i_k = nFAkC \quad (8)$$

Information about the dominant mechanistic pathway at a given potential value can be elucidated based on the presence of H_2O_2 detected at the ring (WE2). The data presented in Figure 1 indicates that ORR proceeds via a mixture of the four-electron and two-electron pathways at potential values within the mass transfer limited plateau. At potential values less than -0.10 the two-electron mechanism becomes dominant, as evidenced by the increase in H_2O_2 detected at the ring.

It is possible to calculate the diffusion coefficient of oxygen in the system using the slope value from the linear regression applied to the Levich plot in Figure 2. The variables relating to the system that are required for this calculation are listed in Table 1. The concentration of O_2 in the electrolyte is assumed to be equal to its solubility; in other words the solution is saturated. This experiment yields a diffusion coefficient value for oxygen in the electrolyte of $7.6 \times 10^{-5} \text{ cm}^2 \text{ s}^{-1}$ when assuming a four-electron process and $2.2 \times 10^{-5} \text{ cm}^2 \text{ s}^{-1}$ when assuming two electrons are transferred. In reality, both processes contribute to the measured electrochemical signal. The diffusion coefficient value is high

when compared with a literature value of $1.4 \times 10^{-5} \text{ cm}^2 \text{ s}^{-1}$. This property is sensitive to experimental parameters such as the concentration of O_2 in the electrolyte, which is likely to be the most significant source of uncertainty in this measurement.

Table 1. System variables for the oxygen reduction reaction in 0.5 M H_2SO_4 electrolyte at room temperature.

Parameter	Value	Unit
Kinematic viscosity	0.010	$\text{cm}^2 \text{ s}^{-1}$
Solubility of O_2	1.1×10^{-6}	mol cm^{-3}
Electrode geometric area	0.20	cm^2

Conclusions

In this application note, the Autolab RRDE system was used to study the oxygen reduction reaction with a Pt disk/Pt ring electrode. The H_2O_2 formed at the disk electrode during ORR was detected at the ring electrode; its presence was used as an indicator of the reaction pathway. The Levich and Koutecký-Levich plots were fitted using linear regression. The resulting equations can be used to calculate the diffusion coefficient O_2 in the electrolyte, the number of electrons transferred during the reaction, and the rate constant for electron transfer.

References

- N.A. Anastasijević et al. J. Electroanal. Chem. 229 (1987) 305
- Nenad M. Marković et al. J. Phys Chem. 99 (1995) 3411
- Carlos M. Sánchez- Sánchez and Allen J. Bard. Anal. Chem. 81 (2009) 8094
- Francisco J. Vidal-Iglesias et al. Electrochem. Commun. 15 (2012) 42.
- Alfred B. Anderson. Electrocatal. 3 (2012) 176.
- K-L. Hsueh et al. Electrochimica Acta. 28 (1983) 691.

27 December 2016